

TECHNICAL DATA SHEET

PTFE G400

Properties	Unit	Method	Data - Moulded
<b>PHYSICAL - MECHANICAL</b>			
Density	g/cm <sup>3</sup>	ASTM D792	2,14 - 2,18
Hardness - Shore D	/	ASTM D2240	≥ 51
Tensile Strength - CD	N/mm <sup>2</sup>	ISO 527 v = 50mm/min microtensile die	≥ 24
Elongation at break - CD	%	ISO 527 v = 50mm/min microtensile die	≥ 250
Compressive strength at 1% deformation - CD	N/mm <sup>2</sup>	ASTM D695	4 - 5
Deformation under load at room temperature after 24 hours at 13,7 N/mm <sup>2</sup> - CD	%	ASTM D621	≤ 17
Permanent deformation as above after 24 hours of rest at room temperature - CD	%	ASTM D621	≤ 9
Deformation under load at 260 °C after 24 hours at 41 N/mm <sup>2</sup> - CD	%	ASTM D621	≤ 32
Permanent deformation as above after 24 hours of rest at room temperature - CD	%	ASTM D621	≤ 19
Impact strength Izod	J/m	ASTM D256	153
<b>TRIBOLOGICAL</b>			
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,06
Wear factor K	/	ASTM D3702	2.900
PV limit at 3 m/min at 30 m/min at 300 m/min	N/mm <sup>2</sup> • m/min	/	2,4 4,2 5,7
<b>THERMAL</b>			
Service Temperature (min - max)	°C	/	- 200 / + 260
Thermal expansion coefficient (linear) 25 - 100°C	10 <sup>-5</sup> (mm/mm)/ °C	Similar to ASTM D696	12 - 13
<b>ELECTRICAL</b>			
Dielectric strength (specimen 0,5 mm thick)	KV/mm	ASTM D149	≥ 40
Dielectric Constant at 60 Hz and 10 <sup>6</sup> Hz	/	ASTM D150	2,05 - 2,10
Volume Resistivity	Ω • cm	ASTM D257	10 <sup>18</sup>
Surface Resistivity	Ω	ASTM D257	10 <sup>17</sup>

CD=Cross Direction

The data we are herewith providing are all based on laboratory testing and are proposed to technical designers as possible and useful advice. Deviations from the values hereabove indicated may occur, but they do not constitute themselves either detriment of quality or reason for rejection.

REV. 06 April 2011



**GUARNIFLON SPA**  
(Società Socio Unico soggetta all'attività di direzione e coordinamento ex art. 2497 bis C.C. da parte di Mazza Holding srl)  
Via T. Tasso n. 12 - 24060 Castelli Calepio (BG) ITALY  
VAT N° IT 01406020162  
C.F. 01406020162  
REG.IMPRESSE DI BG - REA N. 203233  
CAPITALE SOCIALE € 10.000.000 interamente versato

PTFE Products Division

Phone +39.035.4494311  
Domestic Dept. Fax +39.035.4425191  
Export Dept. Fax +39.035.4425238

PTFE Finished and Semifinished products  
http://www.guarniflon.com - info@guarniflon.com  
Accounting Dept. fax +39.035.4425249



UNI EN ISO 9001:2008

