

TECHNICAL DATA SHEET

**PTFE G663**

Properties	Unit	Method	Data - Moulded
<b>PHYSICAL - MECHANICAL</b>			
Density	g/cm <sup>3</sup>	ASTM D792	2,28 - 2,36
Hardness - Shore D	/	ASTM D2240	≥ 56
Tensile Strength - CD	N/mm <sup>2</sup>	ISO 12086 ISO 527	≥ 18
Elongation at break - CD	%	ISO 12086 ISO 527	≥ 180
Compressive Yield strength (Offset 1%)	Mpa	ASTM D695	≥ 13,5
Deformation under load at room temperature 24 Hours at 13,7 N/mm <sup>2</sup> - CD	%	ASTM D621	≤ 7,5
Permanent deformation as above after releasing of 24 hours at room temperature - CD	%	ASTM D621	≤ 5
<b>TRIBOLOGICAL</b>			
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,20 - 0,30
Wear factor	mm <sup>3</sup> /N*m*10 <sup>-7</sup>	ASTM D3702	10 - 20
<b>THERMAL</b>			
Service Temperature (min - max)	°C	/	- 200 / + 260
CD = cross direction			
The data we are herewith providing are all based on laboratory testing and are proposed to technical designers as possible and useful advice. Deviations from the values hereabove indicated may occur, but they do not constitute themselves either detriment of quality or reason for rejection.			

REV. 02

April 2015

