

## DMH 180 PU 93

### Mechanical, Physical and Thermal Properties

thermoplastic polyurethane

properties	condition	standard	unit	unit	unit	
colour				green	green	
hardness	23°C	ISO 868	Shore A	<b>93 ± 2</b>	Shore A	<b>93 ± 2</b>
hardness	23°C	ISO 868	Shore D	<b>47 ± 3</b>	Shore D	<b>47 ± 3</b>
modulus 100%	23°C	DIN 53 504	MPa	≥ 13	psi	≥ 1880
modulus 300 %	23°C	DIN 53 504	MPa	≥ 23	psi	≥ 3330
tensile strength	23°C	DIN 53 504	MPa	≥ 50	psi	≥ 7250
elongation at break	23°C	DIN 53 504	%	≥ 500	%	≥ 500
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 100	lbf/inch	≥ 570
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	<b>1200</b>	g/cm <sup>3</sup>	<b>1,2</b>
abrasion	23°C	DIN 53 516	mm <sup>3</sup>	<b>35</b>	mm <sup>3</sup>	<b>35</b>
compression set	*	ISO 815	%	≤ 25	%	≤ 25
compression set	**	ISO 815	%	≤ 33	%	≤ 33
minimum service temperature			°C	<b>-30</b>	°F	<b>-22</b>
maximum service temperature			°C	<b>110</b>	°F	<b>230</b>

\* 24h 70°C 25% def.

\*\* 24h 100°C 25% def.

### Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 10-2014

## DMH

SOLUTION FOR SEALS

### DMH 180 PU 93

#### Mechanical, Physical and Thermal Properties

thermoplastic polyurethane

properties	condition	standard	unit	green	unit	green
colour				green		green
hardness	23°C	ISO 868	Shore A	93 ± 2	Shore A	93 ± 2
hardness	23°C	ISO 868	Shore D	47 ± 3	Shore D	47 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 13	psi	≥ 1880
modulus 300 %	23°C	DIN 53 504	MPa	≥ 23	psi	≥ 3330
tensile strength	23°C	DIN 53 504	MPa	≥ 50	psi	≥ 7250
elongation at break	23°C	DIN 53 504	%	≥ 500	%	≥ 500
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 100	lbf/inch	≥ 570
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	1200	g/cm <sup>3</sup>	1,2
abrasion	23°C	DIN 53 516	mm <sup>3</sup>	35	mm <sup>3</sup>	35
compression set	*	ISO 815	%	≤ 25	%	≤ 25
compression set	**	ISO 815	%	≤ 33	%	≤ 33
minimum service temperature			°C	-30	°F	-22
maximum service temperature			°C	110	°F	230

\* 24h 70°C 25% def.

\*\* 24h 100°C 25% def.

#### Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 10-2014

#### DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch Industriepark West 11

T: +43 (0)3833/200 60-0 F: +43 (0)3833/200 60-500

E: office@dmh.at www.dmh.at

